

TAPAZUL (CG2)

Cementitious tile grout



What is this product

- It's a grout for 1 to 15 mm joints between tiles.

Suitable for any kind of tiles refilling and sealing
Available in white and in colours.
Special colours can be done after development.

Characteristics

- Monocomponent (only needs water)
- 1-15 mm joint widths
- Excellent workability and easy application
- High hardness and frost resistant
- Hydrofuge



How to prepare

- 1- Pour the water first and then, the paste.
- 2- Mix in bowls in an approximated proportion of 2 litres each 5 kgs.
- 3- It's very important to not add more water than recommended, physical and chemical conditions of the product would be then, reduced.
- 4- Hand mix or with a mixer machine (better slow, 500 rpm) until getting a creamy paste.
- 5- Let it settle during 5 minutes before application, in order to additives to act correctly and the, mix again before use.
- 6- Never add water after the paste settles.

How to use

- Rejointment must be done after 24 hours of the ceramics fixing.
- Clean all the rests of adhesive from the joints.
- Mix 'Tapazul' until getting a creamy paste without lumps.
- Fill the joints with product; this operation can be done with different tools: Brush, filling gun, gum spatula...
- Once the joints are filled, let the product settle until it starts getting hard, when the product rests will be cleaned with a sponge.
- After 24 hours of the rejointment, the surface can be cleaned with a wet cloth.

Where to use

- Rejointment of tiles joints of all kind, for interiors or exteriors, specially indicated for minimum distance placing and for joints of until 15 mm.

Joints must be clean and dry.

Technical Data: Tapazul CG2

Aspect	Powder
Presentation	5 kgs bag
Joint width	from 1 to 15 mm
Output	(*)
Retraction	1,39 mm/m
Mixing water	2-2,5 litres each 6 kg
Open time	4 - 6 hours
Temperature during application	min 5°C, max 32°C
Thermal resistance	from -5°C to 80°C
Resistance to flexion	6,2 N/mm2
Resistance to compression	25,0 N/mm2
Absorption	240 min: 0,45 gr
Stockage (from manufacture date, under cover, in a dry place)	12 months



(*) Output: TAPAZUL output changes according to width in cm (A), length in cm (B) and thickness in mm (C) of the tile and to joint width in mm (D). To calculate outputs, follow this formula:

$$\frac{A+B}{A \times B} \times C \times D \times 0,17 = \text{kg/m}^2$$

Composition

- Cement
- Organic and unorganic additives
- Impermeabilizers and plastifiers

Precautions

Product components are not toxic.
It must be worked with gloves, avoid powder inhalation and contact with eyes and skin.
Keep away from children or animals.

First Aid

Skin: Wash with plenty of water
Eyes: Wash with plenty of water
Ingestion: Rinse with water and drink plenty of water

This technical data is written according to our knowledge and essays and doesn't assume any commitment. It's on customer's responsibility the admission and control in the distributor's warehouse or construction, as well as the election of the product to be used on each case. Manufacturer's responsibility is limited to manufacturing defects and for the value of the merchandise because it's out of his control the material election and the working conditions. Technical data for 2019.



Headquarters: Camino Viejo de Simancas, Km. 4 - 47008 Valladolid (Spain) / telf: +34 983 47 52 12
papresa@papresa.net - www.papresa.net

TAPAZUL