

SHIKKUI 1,5

Ultrawhite flexible finish paste



What is this product

- It is a special calcium carbonate finish mortar, extra white, to apply on brick walls, concrete blocks, mortars. Leaves a rough white finish with a high resistance, endurance and flexibility.

Characteristics

- Easy application by hand.
- Extra whiteness.
- Extra flexibility to avoid cracks on extreme conditions.
- Hidrofuge: Protects against humidity.
- Monocomponent.
- Interior and exterior use.



How to prepare

- 1- This product is specially designed to be applied by hand.
- 2- Mix PAPRESA SHIKKUI 1,5 with 6-7 litres of clean water by each 25 kg bag.

How to use

- Mix PAPRESA SHIKKUI 1,5 with water, better with slow mixing machine until getting a creamy paste.
- Apply with trowel.
- Resultant coat width must be between 1 and 6 mm.

Technical Data: Papresa Shikkui 1,5

Aspect	White Powder
Presentation	25 kgs bag
Output	6-7 kg/m ²
Mix water	+/- 25%
Coat width	1-6 mm
Open time	20 minutes
Density	1637 kg/m ³
Ceramic substrate adherence	1,5 N/mm ²
Concrete substrate adherence	1,9 N/mm ²
Resistance to compression	30,4 N/mm ²
Water absorption coefficient	0,2 kg/m ² x min0,5
Water absorption 24 hours	4,3%
Water steam permeability	$\mu = 7,1$
Temperature during application	min 3°C, max 30°C
Fire Reaction	A1
Stockage (from manufacturing date, under cover, in a dry place)	12 months



Composition

- White cement
- Calcium carbonate
- Additives

Precautions

Product components are not toxic. It must be worked with gloves, avoid powder inhalation and contact with eyes and skin. Keep away from children or animals.

First Aid

Skin: Wash with plenty of water
Eyes: Wash with plenty of water
Ingestion: Rinse with water and drink plenty of water

This technical data is written up according to our knowledge and essays and doesn't assume any commitment. It's on customer's responsibility the admission and control in the distributor's warehouse or construction, as well as the election of the product to be used on each case. Manufacturer's responsibility is limited to manufacturing defects and for the value of the merchandise because it's out of his control the material election and the work conditions. Technical data for 2018.

