

PANZER TABIQUE

Mortar glue specially indicated for large format brick fixing



What is this product

- It's a grey cement-glue, ready to fix large format bricks in exteriors and in dampness risk zones (kitchen, bathroom, storage rooms, cellars...)
- For wall with high-medium absorption ceramics, thick coat (6-15 mm), on bricks and cement substrates.



Characteristics

- Monocomponent cement-glue (only needs water)
- Slip resistant
- Thick coat application
- Excellent workability by its thickness and plasticity
- High frost resistance

How to prepare

- 1- Pour the water first and then, the cement-glue.
- 2- Mix in bowls in an approximated proportion of 7 litres each 25 kgs.
- 3- It is very important to not add more water than recommended, because physical and chemical conditions would be then, reduced.
- 4- Hand mix or with a mixer machine (better slow, 500 rpm) until getting a creamy paste.
- 5- Let it settle for 5 minutes for the additives to act correctly and then, mix again before use.
- 6- Never add more water after the paste settles.

How to use

- For wall building
- Prepare the paste as indicated
- Extend the product with the trowel over the ceramic pieces, for making the assembly in the usual way.
- For ceramic fixing (walls).
- Substrate must be clean and dry.
- Apply the product with the dented trowel (no. 6-15) in 1,5 - 2 m² squares
- Check that no surfacial film is formed over the adhesive (in such a case, pass the trowel with some fresh product).

Where to use

- Ceramic walls building with large format and traditional bricks, for interiors and exteriors.
- Using substrates:** Cement, cement-lime mortar, brick and cement floors.
- Substrates must be solid, hard, clean, dry and without deformations.

Do not use: On metal, concrete or wood

Technical Data: Panzer Tabique

Aspect	Grey Powder
Presentation	25 kgs bag
Bulk density	1,6 gr/cm ³
Coat thickness in walls	from 6 to 15 mm
Output in walls	from 5 to 6 kgs/m ²
Mixing water	6-6,5 litres each 25 kgs
Open time according to UNE EN 1346	20 minutes
Waiting time to cut the remaining product (in walls)	10 minutes
Temperature during application	min 5°C
Reaction to fire	A1
Resistance to compression	M10
Stockage (from manufacturing date, under cover, in a dry place)	12 months



Composition

- Grey cement
- Siliceous soils
- Additives and resines

Precautions

Product components are not toxic.
It must be worked with gloves, avoid powder inhalation and contact with eyes and skin.
Keep away from children or animals.

First Aid

Skin: Wash with plenty of water
Eyes: Wash with plenty of water
Ingestion: Rinse with water and drink plenty of water

This technical data is written according to our knowledge and essays and doesn't assume any commitment. It's on customer's responsibility the admission and control in the distributor's warehouse or construction, as well as the election of the product to be used on each case. Manufacturer's responsibility is limited to manufacturing defects and for the value of the merchandise because it's out of his control the material election and the working conditions. Technical data for 2018.



Headquarters: Camino Viejo de Simancas, Km. 4 - 47008 Valladolid (Spain) / telf: +34 983 47 52 12
papresa@papresa.net - www.papresa.net

PANZER